

DHDC-0690ZP-HB

Epoxy anti-corrosive primer, high build



This paint is an anti-corrosive paint made by using zinc phosphate, an excellent anti-corrosive pigment, and epoxy-modified polyamide resin. This paint has an excellent anti-corrosive effect when applied to steel structures and is widely used as an primer of general epoxy paints. It can be used as an primer for the surface of hot dip (electro) galvanized coating.

Usage

Anti-corrosive primer for steel structures and zinc plated steel surfaces requiring long-term anti-corrosion

Specification

Paint type	Epoxy modified polyamide / Anti-corrossive primer / High build (Two-Component)			
Drying time	Category	5°C	20°C	30°C
	Set-to-touch	2 hours	1 hour	40 minutes
	Dry-hard	20 hours	10 hours	8 hours
	Over-coat (Min.)	32 hours	15 hours	12 hours
	Over-coat (Max.)	4 months	3 months	2 months
	Maturation time	1 hour	30 minutes	20 minutes
	Pot life	16 hours	12 hours	8 hours
Thinner	DR-100	Dilution ratio	▷ Brush, roller coating: less than 15%	
Specific gravity	Approx. 1.3(Based on reddish brown)		▷ Airless, spray coating: less than 10%	
Theoretical Coverage	5.2 m ² /ℓ (1time - 100μm)	Solid volume ratio	Approx. 52±1%	
Color	Gray, other colors	Thickness of dried film	100μm	
Mixing ratio	Base(A)/Hardener(B)=3/1 (Volume ratio)	Flash point	At least 7°C	
Gloss	Matte	Shelf life	12 months (Dry, cool, and dark place with good ventilation)	

Product Properties (Physical Property Data)

Excellent film property	Water resistance, oil resistance, and anti-corrosive properties are excellent, and it can be applied to the inside of crude oil or water tanks.
Primer of galvanized surfaces	Applicable for the primer of hot-dip (electro) galvanized surfaces

How to Use

Surface treatment	<ol style="list-style-type: none">1. Completely remove oil, moisture, sand, dust, and other foreign matter from the surface to be coated. The degree of surface treatment to obtain an excellent steel protection effect should be at least SSPC-SP 10 or Sa2.5 (near white metal blast cleaning).The surface roughness should not exceed 75 μm.2. For steel, apply immediately after surface treatment.3. After primer coating, clean up the welded areas (blackened and rusted areas) with a disc sander. Then, touch up with this paint and continue coating.
Coating Method	<ol style="list-style-type: none">1. Although coating can be done by either brush or airless spraying, airless spray coating is best.2. Airless spray coating:<ul style="list-style-type: none">- Tip diameter : 0.019"~0.025"- Injection pressure : More than 2500 P.S.I.(176kg/cm²)- Store the coating equipment after cleaning with an exclusive thinner immediately after use.
Preceding & Follow-up Coating	<ol style="list-style-type: none">1. Follow-up coating : Epoxy resin, urethane resin, PVDF paint are suitable.
Remarks	<ol style="list-style-type: none">1. Sufficient performance after last coating is achieved after drying for 7 days at 20°C.2. For coating areas exposed to the outside, yellowing and chalking may occur in a short period of time due to the effect of sunlight. Upon coating for areas exposed to the outside, be sure to apply top coat.