

EASYTEX 200

Exterior water-based paint



This paint is a water-based paint for exterior finishing of concrete buildings, which is manufactured by selecting acrylic emulsion and pigment with excellent weather resistance. It is an economical exterior water-based paint suitable for new buildings (e.g., concrete mortar, P.C, plaster, etc.) or for repair painting due to its beautiful exterior of dry coated film, good alkali resistance, water resistance and durability and excellent painting workability using a roller or spray.

Usage

Finish coating for exterior walls of alkaline material such as concrete, cement mortar, P.C., plaster, etc.

Specification

Paint type	Acrylic emulsion water-based exterior / Top coat			
Drying time	Category	5℃	20℃	30℃
	Set-to-touch	1 hour	30 minutes	20 minutes
	Dry-hard	3 hours	1 hour	40 minutes
	Time required for re-coating (min.)	6 hours	3 hours	2 hours
Thinner	Tap water(dilution rate: up to 20%, volume ratio)		Coating Method	Brush, roller, spray coating
Specific gravity	Approx. 1.43(based on white color)		Solid volume ratio	Approx. 35%(based on white color)
Theoretical Coverage	5~7㎡/ℓ/2times		Thickness of dried film	60μm (2coats recommended)
Re-coating interval	20℃, sufficient ventilation for a minimum of 3 hours		Color	White
Gloss	Matte			
Storage and preservation	12 months (Dry, cool, and dark place with good ventilation, room temperature 5℃~30℃, humidity less than 80%)			

Product Properties (Physical Property Data)

Price competitiveness	It is a product with excellent economic feasibility at a reasonable price.
Excellent film property	Alkali resistance, durability and water resistance are excellent.

How to Use

Surface treatment	<ol style="list-style-type: none">1. The material should be sufficiently cured (cured more than 30 days at 20°C)2. Laitance, dust, oil and other contaminants on the surface must be completely removed.3. The proper pH of the material must be less than 9, and the percentage of moisture content must be less than 6%.4. The gaps and grooves on the surface must be filled with exterior water-based putty, and surface adjustment should be made before coating.
Coating Method	<ol style="list-style-type: none">1. Primer<ol style="list-style-type: none">① After surface treatment, dilute the water-based permeable sealer DNX-4001 with water up to 100%, and apply once at a dry film thickness of 15μm with a roller or brush.② For areas where the absorption of the surface is severe, apply once more coating.2. Top Coat<ol style="list-style-type: none">① After at least 3 hours at 20°C following undercoating, apply this paint twice to get a dry film thickness of 60μm with a brush, roller or spray.② At this time, apply by diluting with water up to 20%.③ After 2 coats, the re-coating interval is at least 3 hours after the first top coating at 20°C.